

## Influence of C doping on the fracture mode and abrasive wear of Al<sub>2</sub>O<sub>3</sub>Type:

Type:  
Article

Abstract:

Previous studies have shown that the addition of SiC nanoparticles to Al<sub>2</sub>O<sub>3</sub> changes the fracture mode from intergranular to transgranular and in doing so improves the wear resistance. The reason for this is not clear but a change to the grain boundary chemistry caused by impurities such as C added with the SiC may be involved. The aim of the current study was to investigate the influence of small amounts of C doping on the fracture mode and wear properties of Al<sub>2</sub>O<sub>3</sub>. The microstructure and properties of Al<sub>2</sub>O<sub>3</sub> doped with 0 and 0.012 wt% C were studied. Al<sub>2</sub>O<sub>3</sub> showed mainly intergranular fracture. The addition of 0.012 wt% C to Al<sub>2</sub>O<sub>3</sub> changed the fracture mode to mainly transgranular. The wear resistance improved and the percentage of surface grains pulled out was lower compared to pure Al<sub>2</sub>O<sub>3</sub>.

Author	<ul style="list-style-type: none"><li>• Yahya, N. A.</li><li>• Todd, R. I.</li></ul>
Source	Journal of the European Ceramic Society
ISSN	0955-2219
DOI	10.1016/j.jeurceramsoc.2012.07.003
Volume (Issue)	32(16)
Page	4003-4007
Year	2012

Keyword:

Al<sub>2</sub>O<sub>3</sub>, Al<sub>2</sub>O<sub>3</sub>/C, Fracture mode, Abrasive wear, Wear resistance, Pullout, alumina/silicon carbide nanocomposites, alumina, microstructure, behavior, silicon, ceramics, carbon

Please Cite As:

YAHYA, N. A. & TODD, R. I. 2012. Influence of C doping on the fracture mode and abrasive wear of Al<sub>2</sub>O<sub>3</sub>. *Journal of the European Ceramic Society*, 32, 4003-4007.

URL:

- <http://apps.webofknowledge.com> search via Accession No >> 000310392600005
- <http://www.sciencedirect.com/science/article/pii/S0955221912003986>